

**IPACK STRONG PRO**  
**MACHINE FINISHED PAPER**  
**100% BLEACHED KRAFT PULP**

Paper made of bleached ECF kraft pulp (elementary chlorine free). Properly selected fiber composition gives the paper very good strength. Intended for the production of various packaging applications that protect and promote goods, consumers use every day. Meets very demanding expectations of **FLOUR and SUGAR BAGS'** producers as well as requirements for automatic filling. Can be used but not limited to the following applications:

- **Block bottom bags**
- **Flat / gusset bags**
- **Take away and shopping bags**
- **Multilayer bags**
- **Base paper for barrier coating**



Parameter		Method	Typical Values			
Basis Weight (g/m <sup>2</sup> )		ISO 536	60	70	75	80
Moisture Content (%)		ISO 287	6,0			
Tensile Strength (kN/m)	MD	ISO 1924-3	6,5	6,9	7,1	7,2
	CD		3,0	3,2	3,3	3,4
Opacity (%)		ISO 2471	69	73	75	78
Air Resistance (s)		ISO 5636-5	35			
Burst Strength (kPa)		ISO 2758	300			
Water absorptiveness COBB60 (g/m <sup>2</sup> )		ISO 535	25			
Brightness ISO C/2° (%)		ISO 2470-1	88			
Bendtsen roughness (ml/min)		ISO 8791-2	180	200	220	230

MD – Machine Direction / CD – Cross Direction

**IN COMPLIANCE WITH:**

BfR XXXVI	✓
Regulation (EC)no 1935/2004	✓
Directive 94/62/EC	✓
Good Manufacturing Practice	✓
EN 71-3	✓
FDA §§ 176.170	✓
FDA §§ 176.180	✓

**CERTIFICATES:**

FSC®	On request
PEFC™	On request
Quality Management System ISO 9001	✓
Environmental Management System ISO 14001	✓
Safety Management System ISO 45001	✓
Energy Management System ISO 50001	✓
ISEGA (contact with dry, moist and fatty foodstuffs)	✓
PZH	✓